## PAPER

## Magnetic order of Nd<sub>5</sub>Pb<sub>3</sub> single crystals

To cite this article: J-Q Yan et al 2018 J. Phys.: Condens. Matter 30 135801

View the article online for updates and enhancements.



This content was downloaded from IP address 128.219.49.13 on 02/03/2018 at 14:26

J. Phys.: Condens. Matter 30 (2018) 135801 (8pp)

#### https://doi.org/10.1088/1361-648X/aaaf3e

# Magnetic order of Nd<sub>5</sub>Pb<sub>3</sub> single crystals

## J-Q Yan<sup>1,2</sup>, M Ochi<sup>3</sup>, H B Cao<sup>4</sup>, B Saparov<sup>5</sup>, J-G Cheng<sup>6</sup>, Y Uwatoko<sup>7</sup>, R Arita<sup>8</sup>, B C Sales<sup>1</sup> and D G Mandrus<sup>1,2</sup>

<sup>1</sup> Materials Science and Technology Division, Oak Ridge National Laboratory, Oak Ridge, TN 37831, United States of America

<sup>2</sup> Department of Materials Science and Engineering, University of Tennessee, Knoxville, TN 37996, United States of America

<sup>3</sup> Department of Physics, Osaka University, Toyonaka, Osaka 560-0043, Japan

<sup>4</sup> Quantum Condensed Matter Division, Oak Ridge National Laboratory, Oak Ridge, TN 37831, United States of America

<sup>5</sup> Department of Chemistry and Biochemistry, Stephenson Life Sciences Research Center, University of Oklahoma, Norman, OK 73019, United States of America

<sup>6</sup> Beijing National Laboratory for Condensed Matter Physics, and Institute of Physics, Chinese Academy of Sciences, Beijing 100190, People's Republic of China

<sup>7</sup> The Institute for Solid State Physics, The University of Tokyo, Kashiwa, Chiba 277-8581, Japan

<sup>8</sup> RIKEN Center for Emergent Matter Science, 2-1 Hirosawa, Wako, Saitama 351-0198, Japan

## E-mail: yanj@ornl.gov

Received 15 November 2017, revised 4 February 2018 Accepted for publication 14 February 2018 Published 2 March 2018



## Abstract

We report millimeter-sized Nd<sub>5</sub>Pb<sub>3</sub> single crystals grown out of a Nd–Co flux. We experimentally study the magnetic order of  $Nd_5Pb_3$  single crystals by measuring the anisotropic magnetic properties, electrical resistivity under high pressure up to 8 GPa, specific heat, and neutron single crystal diffraction. Two successive magnetic orders are observed at  $T_{N1} = 44$  K and  $T_{N2} = 8$  K. The magnetic cells can be described with a propagation vector k = (0.5, 0, 0). Cooling below  $T_{N1}$ , Nd1 and Nd3 order forming ferromagnetic stripes along the b-axis, and the ferromagnetic stripes are coupled antiferromagnetically along the a-axis for the k = (0.5, 0, 0) magnetic domain. Cooling below  $T_{N2}$ , Nd2 orders antiferromagnetically to nearby Nd3 ions. All ordered moments align along the crystallographic *c*-axis. The magnetic order at  $T_{N1}$  is accompanied by a quick drop of electrical resistivity upon cooling and a lambda-type anomaly in the temperature dependence of specific heat. At  $T_{N2}$ , no anomaly was observed in electrical resistivity but there is a weak feature in specific heat. The resistivity measurements under hydrostatic pressures up to 8 GPa suggest a possible phase transition around 6 GPa. Our first-principles band structure calculations show that Nd<sub>5</sub>Pb<sub>3</sub> has the same electronic structure as does  $Y_5Si_3$  which has been reported to be a one-dimensional electride with anionic electrons that do not belong to any atom. Our study suggests that  $R_5Pb_3$  (R = rareearth) can be a materials playground for the study of magnetic electrides. This deserves further study after experimental confirmation of the presence of anionic electrons.

Keywords: electride, magnetic order, neutron diffraction, specific heat, magnetic structure, high pressure

(Some figures may appear in colour only in the online journal)

## Introduction

The intermetallic compounds  $R_5Pb_3$  (R = rare earth) crystallize in the Mn<sub>5</sub>Si<sub>3</sub>-type hexagonal structure with the space group  $P6_3/mcm$  [1]. In this structure, the rare earth ions are located at two inequivalent crystallographic sites R1(4d) and R2(6g). Pb is located at the octahedral site (6g) only. As shown in figure 1, R1 stays inside of twisted trigonal prisms which share faces along *c*-axis forming a chain and share edges in the *ab*-plane forming a honeycomb array. R2 ions



**Figure 1.** A representation of the hexagonal structure of  $Nd_5Pb_3$  viewed (a) down the *c*-axis, and (b) along *c*-axis. Nd1, Nd2 and Pb atoms are colored as brown, yellow and black spheres, respectively.

are arranged to form a chain of trigonal antiprisms and are connected by sharing basal faces. One interesting feature of this structure is that the void in the center of each trigonal antiprism might host some small foreign ions without destabilizing the hexagonal structure [2]. This stuffing effect leads to a rich interstitial chemistry and affords a novel means of engineering band topology and thus physical properties of a given host. Complex magnetic phase transitions have been reported in  $R_5Pb_3$  and Cu- or Ni-stuffed versions [3–8]. Compared to  $R_5M_3$  (M = Si, Ge, Sn) where interesting magnetism, magnetoresistivity, and heavy fermion behavior have been reported [9–13], the  $R_5Pb_3$  family is less studied and all previous work was done on polycrystalline samples.

 $R_5Pb_3$  attracts our attention also because of Hosono's work on Y<sub>5</sub>Si<sub>3</sub> and Nb<sub>5</sub>Ir<sub>3</sub> with the same Mn<sub>5</sub>Si<sub>3</sub>-type structure [14, 15]. Y<sub>5</sub>Si<sub>3</sub> was confirmed experimentally and theoretically as a one-dimensional electride with 0.79e<sup>-</sup> in the void behaving like anions [14]. In the isostructural Nb<sub>5</sub>Ir<sub>3</sub>, replacing the localized anionic electrons in the voids with oxygen atoms was reported to tune the superconducting transition temperature [15]. With the same structure,  $R_5Pb_3$  can be a new materials playground to investigate possible relation between the physical properties and the anionic electrons.

In this work, we report the first flux growth of Nd<sub>5</sub>Pb<sub>3</sub> single crystals and a thorough investigation of the magnetic order of this compound. Long range magnetic orders are observed at  $T_{N1} = 44$  K and  $T_{N2} = 8$  K, respectively, by measuring the magnetization, electrical resistivity, and specific heat. Our neutron single crystal diffraction shows that the magnetic cells can be described with a propagation vector k = (0.5, 0, 0). We also perform first-principles band structure calculations which suggest that Nd<sub>5</sub>Pb<sub>3</sub> has the same electronic structure as does Y<sub>5</sub>Si<sub>3</sub>. The intrinsic magnetic and transport properties reported in this study enable a reliable comparison between Nd<sub>5</sub>Pb<sub>3</sub> and those stuffed versions to understand possible effects of the interstitial ions in the voids. The reported growth protocol can be applied for the growth of most  $R_5Pb_3$  members which makes possible further studies of their anisotropic and intrinsic physical properties.

#### **Experimental details**

Nd<sub>5</sub>Pb<sub>3</sub> single crystals were grown out of Nd–Co flux [16]. In a typical growth, the starting materials Nd (99.999%, Ames

Laboratory), Co (99.999%, Alfa Aesar), and Pb (99.9999%, Alfa Aesar) were placed in a 2ml alumina crucible with a molar ratio of 7:2:1. A catch crucible containing quartz wool was mounted on top of growth crucible and both were sealed in a silica ampoule under approximately 1/3 atmosphere of argon gas. The sealed ampoule was heated to 1100 °C, dwelled at 1100 °C for 2h, and then cooled to 850 °C over 50h. Once the furnace reached 850 °C, the excess flux was decanted from the crystals.

Room temperature x-ray powder diffraction patterns were collected on a X'Pert PRO MPD x-ray powder diffractometer using Ni-filtered Cu-K<sub> $\alpha$ </sub> radiation. The phase identification was carried out employing X'Pert HighScore Plus software. The elemental analysis was performed using a Hitachi TM-3000 tabletop electron microscope equipped with a Bruker Quantax 70 energy dispersive x-ray (EDX) system.

Magnetic properties were measured with a Quantum Design (QD) Magnetic Property Measurement System in the temperature interval  $1.8 \text{ K} \leq T \leq 320 \text{ K}$ . The temperature dependent specific heat and electrical transport data were collected using a 14 Tesla QD Physical Property Measurement System in the temperature range of  $1.9 \text{ K} \leq T \leq 300 \text{ K}$ . The temperature dependence of electrical resistivity under hydrostatic pressures up to 8 GPa was measured using the standard four-probe method in a cubic-anvil-type apparatus [17].

Single crystal x-ray diffraction measurements were carried out with the aid of a Bruker SMART APEX CCD-based single crystal x-ray diffractometer. A hexagonal needle-shaped crystal was selected under a microscope and cut into suitable dimensions ( $\approx 0.082 \times 0.076 \times 0.070 \text{ mm}^3$ ) inside Paratone N oil. The x-ray intensity data were acquired at 173(2) K with Mo K $\alpha$  ( $\lambda = 0.71073$  Å) radiation. Data collection, integration, and semi-empirical absorption correction based on equivalents were performed using SMART, SAINT and SADABS, respectively, all within the SHELXTL package. The structure refinement was carried out using the SHELXTL software package. Site occupation factors were checked by freeing individual occupancies of atom sites.

Single crystal neutron diffraction was measured at HB-3A four-circle diffractometer at the High Flux Isotope Reactor at the Oak Ridge National Laboratory. A neutron wavelength of 1.546 Å was used with a bent perfect Si-220 monochromator [18]. The data were refined by the Rietveld method using Fullprof [19].

#### Results

#### Crystal growth and characterization

As described before [16], the alumina crucible can oxidize some Nd leading to the growth of Nd<sub>5</sub>Pb<sub>3</sub>O crystals. We noticed that a shorter dwelling time at the homogenizing temperature and a faster cooling rate favor the growth of Nd<sub>5</sub>Pb<sub>3</sub>. Both factors reduce the amount of oxidization and hence the oxygen content in the melt. As shown in inset of figure 2, Nd<sub>5</sub>Pb<sub>3</sub> crystals are normally about 2–3 mm long with a hexagonal cross section, which is different from the rectangular cross section of Nd<sub>5</sub>Pb<sub>3</sub>O crystals. Elemental analysis confirmed the atomic ratio and did



**Figure 2.** Room temperature x-ray powder diffraction of pulverized single crystals. The \* symbol shows two peaks from lead flux on crystal surface. Inset shows the crystal picture and the EDX spectrum showing possible elements in the crystals.

**Table 1.** Structure parameters for Nd<sub>5</sub>Pb<sub>3</sub> with the space group  $P6_3/mcm$  (no. 193) at 173 K. Lattice parameters were determined to be a = 9.2275(9) Å and c = 6.7407(13) Å. The equivalent isotropic displacement parameter  $U_{eq}$  is defined as one third of the trace of the orthogonalized  $U_{ij}$  tensor.

Atom	site	x	у	z	$U_{\rm eq}({\rm \AA}^2)$
Nd1	4 <i>d</i>	1/3	2/3	0	0.0274(4)
Nd2	6 g	0.23130(12)	0	0.25	0.0303(4)
Pb	6 g	0.60214(7)	0	0.25	0.0271(4)

not see any signal from Co. This confirms that Co is one important component in the flux to lower the melting temperature of the melt but does not contaminate the desired crystals [16]. The room temperature x-ray powder diffraction pattern can be indexed with hexagonal  $P6_3/mcm$  symmetry. As highlighted by the asterisks, there are two extra reflections from residual lead flux on crystal surface. This residual flux on the crystal surface leads to zero electrical resistivity observed in some resistivity measurements below 7K when Pb superconducts.

Nd<sub>5</sub>Pb<sub>3</sub>O has a tetragonal structure (space group *I*4/*mcm*). There is no report whether a critical amount of O content,  $x_c$ , is needed in Nd<sub>5</sub>Pb<sub>3</sub>O<sub>x</sub> to induce the lattice symmetry change from the hexagonal *P*6<sub>3</sub>/*mcm* to the tetragonal *I*4/*mcm*. To confirm our crystals are oxygen free Nd<sub>5</sub>Pb<sub>3</sub> instead of hexagonal Nd<sub>5</sub>Pb<sub>3</sub>O<sub>x</sub> with  $x < x_c$ , we performed single crystal x-ray and neutron diffraction studies. The structure refinement does not provide any evidence for the partial occupancy of oxygen in the voids of Nd trigonal antiprisms. Table 1 shows the refined structure parameters from x-ray single crystal diffraction at 173 K. Partial occupation of the voids by oxygen is further confirmed by neutron single crystal diffraction which can better resolve the oxygen occupation.

#### Magnetic properties

Figure 3 shows the temperature dependence of magnetic susceptibility in a magnetic field of 10 kOe applied parallel and



**Figure 3.** Temperature dependence of magnetic susceptibility and inverse magnetic susceptibility measured in a magnetic field of 10 kOe applied parallel and perpendicular to the crystallographic c-axis, respectively.



**Figure 4.** Field dependence of magnetization at different temperatures:  $2 \text{ K} < T_{N2}$ ,  $T_{N2} < 25 \text{ K} < T_{N1}$ , and  $T_{N1} < 60 \text{ K}$ .

perpendicular to the crystallographic *c*-axis. The magnetic susceptibility curves measured in zero-field-cooled (ZFC) mode show a cusp around 8K, and the ZFC and field-cooled (FC) curves split at  $\sim$ 15 K. Above  $\sim$ 20 K, the magnetic susceptibility measured with  $H \perp c, \chi_{\perp}$ , shows a Curie–Weisslike temperature dependence. This is highlighted by the linear temperature dependence of  $1/\chi_{\perp}$ . In contrast, one cusp is observed around 44 K in the magnetic susceptibility measured with  $H \| c, \chi_{\parallel}$ . The plot of  $1/\chi_{\parallel}$  suggests that  $1/\chi_{\parallel}$  deviates from the high temperature linear fitting below  $\sim 160$  K. The linear fitting of  $1/\chi_{\perp}$  in the temperature range  $50 \,\mathrm{K} \leq T \leq$ 300 K yields an effective moment of 4.20  $\mu_{\rm B}/{\rm Nd}$ , and a Weiss constant of -12 K. Due to the slope change around 160 K, the linear fitting of  $1/\chi_{\parallel}$  was performed in two different temperature intervals. The fitting in the temperature range 190K  $\leq T \leq 300$  K yields an effective moment of 4.24  $\mu_{\rm B}$ /Nd, and a Weiss constant of -0.3 K. The fitting of the low temperature data in the temperature range  $50 \text{ K} \leq T \leq 150 \text{ K}$  yields an effective moment of 3.92  $\mu_{\rm B}/{\rm Nd}$ , and a Weiss constant of 24 K. The obtained effective moments are a little larger than the expected 3.62  $\mu_{\rm B}/{\rm Nd}$  for  ${\rm Nd}^{3+}$  ions. The temperature dependence of magnetic susceptibility suggests two magnetic transitions at  $T_{N1} = 44$  K and  $T_{N2} = 8$  K, respectively. The data



**Figure 5.** (a) Temperature dependence of specific heat. Upper inset plots the temperature dependence of  $C_p/T$  highlighting the field effect around  $T_{N2} = 8$  K. Lower inset highlights the details around  $T_{N1}$  in three different magnetic fields. Also shown in this panel is the specific heat of La<sub>5</sub>Pb<sub>3</sub>, which is used as phonon reference. (b) The magnetic specific heat,  $\Delta C_p$ , and the entropy change, *S*, across the transitions.

also suggest that antiferromagnetic order is established below  $T_{N1}$  and a weak ferromagnetic component appears below  $T_{N2}$ . The magnetic ordering temperatures are further confirmed by specific heat, electrical resistivity, and neutron single crystal diffraction presented below.

Figure 4 shows the field dependence of magnetization at three different temperatures. At 60 K, magnetization shows a linear field dependence for both  $H \perp c$  and  $H \parallel c$ . At 25 K, a metamagnetic transition was observed around 40 kOe for  $H \parallel c$ , while it is absent for  $H \perp c$ . This suggests that an antiferromagnetic magnetic order occurs between 25 K and 60 K and the magnetic moment is along the crystallographic *c*-axis. At 2K, the magnetization curves show similar anisotropic field dependence as at 25 K. In addition to the metamagnetic transition, the magnetization curves at 2K and 25K show a ferromagnetic component. Linear fits to the M(H) data for H > 20 kOe were performed. The slope of the high field linear fits gives the intrinsic susceptibility, and the H = 0 Oe intercept gives the saturation magnetization of the ordered phases. Cooling from 25 K to 2 K, the intrinsic susceptibility increases from  $3.383(7) \times 10^{-5} \mu_{\rm B} \, {\rm fu}^{-1}$  to  $4.096(3) \times 10^{-5} \, \mu_{\rm B} \, {\rm fu}^{-1}$ , and the saturation magnetization increases from 0.195(3)  $\mu_{\rm B}$  fu<sup>-1</sup> to 0.374(14)  $\mu_{\rm B}$  fu<sup>-1</sup>. This is consistent with the observation



**Figure 6.** Temperature dependence of the electrical resistivity measured with the electrical current parallel to the crystallographic *c*-axis. The magnetic field is applied perpendicular to the *c*-axis. Inset shows the derivative of the electrical resistivity around  $T_{N1}$ .

of the cusp in ZFC  $\chi(T)$  curves and the splitting between ZFC and FC  $\chi(T)$  curves shown in figure 3.

#### Specific heat

Figure 5(a) shows the temperature dependence of specific heat in the temperature range  $1.90 \text{ K} \leq T \leq 200 \text{ K}$  measured in magnetic fields applied perpendicular to the crystallographic c-axis. A lambda-type anomaly can be well resolved with a maximum at 44 K, suggesting that long range magnetic order occurs at this temperature. The transition temperature inferred from specific heat is consistent with that determined from  $\chi_{\parallel}$ . The specific heat data were also collected in applied magnetic fields of 60 kOe and 120 kOe, respectively. The applied magnetic field reduces the magnitude of the lambda-type anomaly and shifts it to lower temperatures. This also supports the conclusion that an antiferromagnetic order occurs at  $T_{N1} = 44$  K. No obvious anomaly can be resolved around  $T_{N2}$  in the temperature dependence of specific heat. However, as plotted in the upper inset of figure 5, the applied magnetic field changes the magnitude of  $C_p/T$  below  $T_{N2} = 8$  K.

To estimate the entropy change across the magnetic order, we scaled the specific heat of La<sub>5</sub>Pb<sub>3</sub> and subtracted it from that of Nd<sub>5</sub>Pb<sub>3</sub>. Figure 5(b) shows the magnetic specific heat,  $\Delta C_p$ , and the entropy change, S, obtained by integrating  $\Delta C_p/T$  from 1.90 K to 200 K. In addition to the anomaly around  $T_{N1} = 44$  K, a weaker feature was observed below 20 K in the temperature dependence of  $\Delta C_p$ . This weak anomaly peaks at about 10 K, which is close to  $T_{N2} = 8$  K determined from magnetic susceptibility curves shown in figure 3. The total entropy change is roughly 46 J (mol K)<sup>-1</sup>, which is about half of the expected  $5R \ln(2J + 1) = 96$  J (mol K)<sup>-1</sup> for Nd<sup>3+</sup>. The entropy change across  $T_N = 44$  K obtained by integrating between 15 K and 200 K is about 32 J (mol K)<sup>-1</sup>.



Figure 7. Temperature dependence of the electrical resistivity under high pressure measured with the electrical current parallel to the crystallographic *c*-axis. The upper inset shows the derivative of the electrical resistivity. The lower inset shows the pressure dependence of  $T_{N1}$  and the dashed curve is a guide to the eyes.

#### Electrical resistivity

Figure 6 shows the temperature dependence of electrical resistivity measured with the electrical current parallel to the crystallographic *c*-axis. Upon cooling, the electrical resistivity decreases from a room temperature value of  $\sim 400 \ \mu\Omega \,\mathrm{cm}^{-1}$ . A sharp drop of resistivity was observed across  $T_{N1}$ , which signals the significantly reduced effect of magnetic scattering on the electron transport. A sharp resistivity drop around 7K is sometimes observed due to the filamentary superconductivity of lead flux on the crystal surface. This resistivity drop can be eliminated by applying an external magnetic field. Figure 6 also shows the temperature dependence of electrical resistivity measured in an applied magnetic field of 40 kOe. It's noteworthy that the magnetoresistive effect is negligible in this field. No anomaly around  $T_{N1} = 8$  K was observed.

Figure 7 shows the effect of hydrostatic pressure up to 8 GPa on the electrical resistivity. High pressure increases the electrical conductivity and broadens the resistivity drop around  $T_{N1}$ . The latter is highlighted by the derivative of electrical resistivity shown in the inset of figure 7. If we define the peak temperature as  $T_{N1}$ , the results suggest a possible pressure-induced phase transition around 6 GPa, which deserves further study. As shown in the inset of figure 7,  $T_{N1}$  decreases with increasing pressure below 6 GPa and then increases with further increasing pressure. As no anomaly could be observed at  $T_{N2}$  in our measurement, the pressure dependence of  $T_{N2}$ remains unknown. We notice the values of resistivity shown in figure 7 are larger than those in figure 6. This discrepancy comes from the uncertainties of measuring the dimension of small crystals used in the measurements.

## Neutron single crystal diffraction

To confirm the magnetic order and to determine the low temperature magnetic structure, we performed a neutron single crystal diffraction study below room temperature. Figure 8 shows the evolution with temperature of the intensity



**Figure 8.** Temperature dependence of the intensity of (0.5 - 10)magnetic reflection.

of the  $(0.5 - 1 \ 0)$  reflection of one Nd<sub>5</sub>Pb<sub>3</sub> single crystal. The evolution suggests two magnetic transitions at  $T_{N1} = 36$  K and  $T_{N2} = 8$  K. We noticed that  $T_{N1}$  varies slightly with samples, which might come from the air sensitivity. The intensity change around 8 K confirms the magnetic origin of the anomalies observed in the temperature dependence of magnetic susceptibility and specific heat.

In order to determine the detailed magnetic structure below  $T_{N1}$  and  $T_{N2}$ , we collected 90 magnetic reflections at 5K and 25 K, respectively. The magnetic cell can be defined with a propagation vector k = (0.5, 0, 0). The best fit magnetic symmetry is PBnma (62.454) [20]. The in-plane magnetic component for the Nd1-site is symmetry allowed but does not improve the refinement. The refined in-plane magnetic moment within the error bar is zero. Therefore, the in-plane magnetic components are fixed to zero in the final refinement. To accommodate with the propagation vector in describing the magnetic structure, the Nd2 site splits to Nd2 (0.2310, 0, 1/4) and Nd3 (0, 0.2310, 1/4). The refined magnetic structures are plotted in figure 9. All Nd moments stay along the crystallographic c-axis. At 25 K, the Nd1 ions at 4d site order with a moment of 2.7(1)  $\mu_{\rm B}/{\rm Nd}$ : the ferromagnetic chains couple antiferromagnetically along the *a*-axis. An ordered moment of 2.1(2)  $\mu_{\rm B}$  was observed on the Nd3 atoms which might be induced by the two ferromagnetically aligned Nd1 ions nearby. The ordered moment is zero on the Nd2 sites, around which two Nd1 ions are coupled antiferromagnetically. As highlighted in figure 9, the ordering of the Nd1 and Nd3 sites form ferromagnetic stripes along the *b*-axis, and the ferromagnetic stripes are coupled antiferromagnetically along the a-axis for the k = (0.5, 0, 0) magnetic domain. Cooling below  $T_{N2}$ , all three Nd sites order with the same magnetic propagation vector. The ordered magnetic moments for Nd1, Nd2, and Nd3 are 3.2(1)  $\mu_{\rm B}$ , -1.1(1)  $\mu_{\rm B}$ , and 1.8(2)  $\mu_{\rm B}$ , respectively.

### Band structure

To check possible anionic states in Nd<sub>5</sub>Pb<sub>3</sub>, we performed first-principles band structure calculations using the density



**Figure 9.** Magnetic structure at (a) 5 K and (b) 25 K. Nd1, Nd2, and Nd3 are in red, blue, and green, respectively. Only Nd ions are shown for clarity. At 25 K, Nd2 ions are shown as solid circles but with zero moment.

functional theory (DFT) with the generalized gradient approximation (GGA) [21] and the full-potential linearized augmented plane-wave method as implemented in the WIEN2K code [22]. We also included +*U* correction [23, 24] for Nd atoms with U = 9 eV. We assumed the experimental antiferromagnetic configuration, and the spin–orbit coupling was not included here for simplicity. The muffin-tin radii ( $R_{\text{MT}}$ ) for Nd, Pb, and H atoms were 2.50, 2.50, and 1.79 Bohr, respectively. The maximum modulus for the reciprocal vectors  $K_{\text{max}}$ was chosen such that  $R_{\text{MT}}K$ max = 8.0 and 5.5 for Nd<sub>5</sub>Pb<sub>3</sub> and Nd<sub>5</sub>Pb<sub>3</sub>H, respectively. Note that the unit cell and the lattice vectors used in calculation are different from those shown in other parts of this paper.

Figures 10(a) and (b) show the calculated band structures of  $Nd_5Pb_3$  and the virtual compound  $Nd_5Pb_3H$  where the hydrogen atoms were located at the same positions as those for  $Y_5Si_3H$  [25], respectively. By comparing their band structures, we can find a characteristic difference between them as



**Figure 10.** Band structures of (a)  $Nd_5Pb_3$  and (b)  $Nd_5Pb_3H$ . The Fermi level is set to zero for each panel. Bloch states indicated with black arrows in (a) and (b) are drawn in (c) and (d) and in (e) and (f), respectively, using the VESTA software [26].

indicated with black arrows. The Bloch states at the  $(0, 0, \pi)$  point indicated with black arrows are shown in figures 10(c) and (d) for Nd<sub>5</sub>Pb<sub>3</sub> and in figures 10(e) and (f) for Nd<sub>5</sub>Pb<sub>3</sub>H. As is evident in these figures, the extra bands in Nd<sub>5</sub>Pb<sub>3</sub> can be regarded as the anion states extended in void space, which are rather localized around hydrogen atoms in Nd<sub>5</sub>Pb<sub>3</sub>H. This situation is the same as that found in Y<sub>5</sub>Si<sub>3</sub> [14].

A sizable difference among the size of the spin magnetic moments on Nd atoms in our experiment was not reproduced by our first-principles calculations assuming the experimental antiferromagnetic configuration using the GGA + U + SOC method even with U = 5 or 7 eV, which result in almost the same size of the spin magnetic moment on every Nd atom. This disagreement suggests that the complex magnetic structure observed in our experiment originates from some effects not included in our simple band structure calculations, such as the strong correlation effects for *f*-electrons or the spin frustration effect for the triangle network among Nd2 atoms.

## Discussion

Our measurements of magnetic properties, electrical resistivity, and specific heat suggest two successive magnetic phase transitions at  $T_{N1} = 44$  K and  $T_{N2} = 8$  K. Cooling from 25 K to 5 K, the ordered magnetic moment of Nd1 ions increases slightly from 2.7(1)  $\mu_{\rm B}$  to 3.2(1)  $\mu_{\rm B}$ , which is the same as the free ion value of  $gJ = 3.27 \ \mu_{\rm B}$ . This indicates that Nd1 is rather localized. In contrast, the ordered magnetic moments on Nd2 (0.2310, 0, 1/4) and Nd3 (0, 0.2310, 1/4) ions are much smaller. The moment variation reflects the effect of different crystal electric fields at different crystallographic sites. Spin frustration effect from the triangle network among Nd2 (0.2310, 0, 1/4) and Nd3 (0, 0.2310, 1/4) ions might also suppress the ordered moments on these two sites.

The results in figures 3 and 4 demonstrate that Nd<sub>5</sub>Pb<sub>3</sub> shows anisotropic magnetic properties. This is consistent with the chain structure formed by the Nd1 and Nd2 ions. The slope change in  $1/\chi_{\parallel}$  observed around 160K is in contrast to the linear temperature dependence of  $1/\chi_{\perp}$  in the paramagnetic state. It is worth mentioning that the Curie–Weiss fitting of  $1/\chi_{\perp}$  gives a negative Weiss constant, suggesting dominant antiferromagnetic interactions. While the fitting of  $1/\chi_{\parallel}$  around 160K signals the development of short range magnetic correlations below 160K.

Neutron single crystal diffraction measurement suggests that both Nd2(0.2310, 0, 1/4) and Nd3 (0, 0.2310, 1/4) order in the temperature interval  $T_{N2} \leq T \leq T_{N1}$ , suggesting Nd–Nd exchange interactions between the two different Nd sites. This should be considered when understanding the effect on magnetic properties of high pressure or interstitial ions in the voids. The coincidence that the ordered Nd3 (0, 0.2310, 1/4)ions have two ferromagnetically aligned Nd1 neighbours indicate that the magnetic order at  $T_{N1}$  is driven by the ordering of Nd1 moments. With increasing pressure, the lattice contraction reduces the distance between magnetic Nd1 ions and nonmagnetic ligand ions which tends to weaken the localized electron magnetism. Above 6 GPa,  $T_{N1}$  shows a positive pressure dependence. While pressure induced nuclear and/or magnetic phase changes are likely, those possible anionic electrons in the voids, once confirmed experimentally, should be considered in future studies. Under high pressure, the anionic electrons can interact with each other and also with nearby Nd ions affecting the magnetic interactions and even the magnetic ground states [27].

Our DFT calculations of the band structure of  $Nd_5Pb_3$ suggest extra bands from the anion states as in  $Y_5Si_3$ . Future experimental studies are needed to confirm the presence of anionic electrons in the voids of  $Nd_5Pb_3$ . However, the comparison between  $Nd_5Pb_3$  and  $Nd_5NiPb_3$  does not seem to suggest any obvious role of anionic electrons in determining the magnetic ordering temperatures. The magnetic and thermodynamic measurements on polycrystalline  $Nd_5NiPb_3$  suggest two magnetic transitions: an antiferromagnetic transition at 42 K, and a weak-ferromagnetic canting transition at 8 K [4]. This similarity implies that filling the voids with nonmagnetic Ni does not affect the magnetic ordering of Nd ions.

#### Summary

In summary, we report the first growth of Nd<sub>5</sub>Pb<sub>3</sub> single crystals and this growth protocol works for most  $R_5Pb_3$  members, which enables the study of the intrinsic and anisotropic properties of this family. We study the magnetic order in Nd<sub>5</sub>Pb<sub>3</sub> single crystals by measuring magnetic and transport properties, specific heat, and neutron single crystal diffraction. Two successive magnetic orders take place at  $T_{N1} = 44 \text{ K}$  and  $T_{N2} = 8$  K. The magnetic cells can be described with a propagation vector k = (0.5, 0, 0). Cooling below  $T_{N1}$ , Nd1 and Nd3 order forming ferromagnetic stripes along b-axis, and the ferromagnetic stripes are coupled antiferromagnetically along a-axis. The coincidence that two nearest Nd1 ions around Nd3 are ferromagnetically aligned and those two around Nd2 are antiferromagnetically coupled suggests that the magnetic orderings of Nd ions on different sublattices are coupled. Below  $T_{N2}$ , Nd2 orders antiferromagnetically to nearby Nd3 ions. The temperature-dependent electrical resistivity shows a quick drop upon cooling below  $T_{N1}$  but no anomaly around  $T_{N2}$ . This suggests little effect on electrical transport from the Nd ions forming the trigonal antiprisms that can host anionic electrons. Band structure calculations show that the anionic states form the band dispersions near the Fermi level, which is similar to the case of Y<sub>5</sub>Si<sub>3</sub>. Future experimental studies are needed to confirm the presence of anionic electrons in the voids and its possible relation with the pressure dependence of  $T_{N1}$ above 6 GPa. Comparison between Nd<sub>5</sub>Pb<sub>3</sub> and Nd<sub>5</sub>NiPb<sub>3</sub> suggests that filling the confined space in the trigonal antiprisms with nonmagnetic Ni does not affect the magnetic properties.

## Acknowledgments

Work at ORNL was supported by the US Department of Energy, Office of Science, Basic Energy Sciences, Division of Materials Sciences and Engineering. The neutron diffraction work at ORNL was sponsored by the US Department of Energy, Office of Science, Basic Energy Sciences, Scientific User Facilities Division. JGC is supported by the National Science Foundation of China (Grant No. 11574377), the National Basic Research Program of China (Grant No.2014CB921500), the Strategic Priority Research Program and Key Research Program of Frontier Sciences of the Chinese Academy of Sciences (Grant Nos. XDB07020100, QYZDB-SSW-SLH013). YU is supported by JSPS KAKENHI (Grant No. 15H03681).

## **ORCID** iDs

J-Q Yan b https://orcid.org/0000-0001-6625-4706

#### References

[1] Jeitschko W and Parthé E 1967 Acta Crystallogr. 22 551

- [2] Corbett J D, Garcia E, Guloy A M, Hurng W-M, Kwon Y-U and Leon-Escamilla E A 1998 Chem. Mater. 10 2824
- [3] Tran V, Gamża M, Ślebarski A, Jarmulska J and Miiller W 2007 J. Solid State Chem. 180 2756
- [4] Goruganti V, Rathnayaka K and Ross J H Jr 2009 J. Appl. Phys. 105 07E118
- [5] Tran V, Jarmulska J and Miiller W 2007 Mater. Sci.-Poland 25 327
- [6] Tran V and Gulay L 2006 J. Solid State Chem. 179 646
- [7] Marcinkova A, de la Cruz C, Yip J, Zhao L L, Wang J K, Svanidze E and Morosan E 2015 *J. Magn. Magn. Mater.* 384 192
- [8] Sasao K, Yamauchi R and Fukamichi K 1999 J. Magn. Soc. Japan 23 489
- [9] Mukherjee K, Iyer K K and Sampathkumaran E 2011 J. Phys.: Condens. Matter 23 066003
- [10] Maji B, Suresh K and Nigam A 2010 Europhys. Lett.
  91 37007
- [11] Tanaka A, Tsutaoka T and Tokunaga T 2006 J. Alloys Compd. 408 184
- [12] Mohapatra N, Mukherjee K, Iyer K K and Sampathkumaran E 2011 J. Phys.: Condens. Matter 23 496001
- [13] Lawrence J, Hundley M, Thompson J, Kwei G and Fisk Z 1991 Phys. Rev. B 43 11057
- [14] Lu Y, Li J, Tada T, Toda Y, Ueda S, Yokoyama T, Kitano M and Hosono H 2016 J. Am. Chem. Soc 138 3970
- [15] Zhang Y, Wang B, Xiao Z, Lu Y, Kamiya T, Uwatoko Y, Kageyama H and Hosono H 2017 npj Quantum Mater. 2 45

- [16] Yan J-Q 2015 J. Cryst. Growth 416 62
- [17] Cheng J-G, Matsubayashi K, Nagasaki S, Hisada A, Hirayama T, Hedo M, Kagi H and Uwatoko Y 2014 *Rev. Sci. Instrum.* 85 093907
- [18] Chakoumakos B C, Cao H, Ye F, Stoica A D, Popovici M, Sundaram M, Zhou W, Hicks J S, Lynn G W and Riedel R A 2011 J. Appl. Crystallogr. 44 655
- [19] Rodríguez-Carvajal J 1993 Physica B 192 55
- [20] Gallego S V, Tasci E S, Flor G, Perez-Mato J M and Aroyo M I 2012 J. Appl. Crystallogr. **45** 1236
- [21] Perdew J, Burke K and Ernzerhof M 1996 Phys. Rev. Lett. 78 1396
   Perdew J, Burke K and Ernzerhof M 1997 Phys. Rev. Lett.
  - Perdew J, Burke K and Ernzerhof M 1997 *Phys. Rev. Lett.* **78** 1396 (erratum)
- [22] Blaha P, Schwarz K, Madsen G, Kvasnicka D and Luitz J 2001 WIEN2k, an Augmented Plane Wave + Local Orbitals Program for Calculating Crystal Properties (Vienna: Karlheinz Schwarz, Technische Universität Wien)
- [23] Liechtenstein A, Anisimov V and Zaanen J 1995 Phys. Rev. B 52 R5467
- [24] Dudarev S, Botton G, Savrasov S, Humphreys C and Sutton A 1998 Phys. Rev. B 57 1505
- [25] Mccolm I, Kotroczo V, Button T, Clark N and Bruer B 1986 J. Less Common Met. 115 113
- [26] Momma K and Izumi F 2011 J. Appl. Crystallogr. 44 1272
- [27] Miao M-S and Hoffmann R 2015 J. Am. Chem. Soc. 137 3631